

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 902 017 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
17.03.1999 Bulletin 1999/11

(51) Int Cl.⁶: **C07D 233/32, C07C 67/03,
C07C 69/54, C07C 67/62,
C07D 263/04**

(21) Application number: **98306833.9**

(22) Date of filing: **27.08.1998**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: **Weir, William David**
Levittown, PA 19056 (US)

(74) Representative: **Tanner, James Percival et al**
ROHM AND HAAS (UK) LTD.
European Operations Patent Department
Lennig House
2 Mason's Avenue
Croydon CR9 3NB (GB)

(30) Priority: **29.08.1997 US 57283 P**
12.08.1998 US 133144

(71) Applicant: **ROHM AND HAAS COMPANY**
Philadelphia, Pennsylvania 19106-2399 (US)

(54) **Transesterification process**

(57) A process which enables the production of various monomers is disclosed. Compounds to prevent the

unwanted polymerization of monomers and monomer compositions containing those compounds are also disclosed.

EP 0 902 017 A1

the solution was cooled to 70°C and to it was added 7.9 grams (0.014 moles) of tetraethylhexyl titanate and 83.2 grams (0.83 moles) of MMA. The solution was stirred, sparged with 8% O₂ - 92% N₂ at a rate of 30 - 35 ml. / min. and heated to reflux under reduced pressure (550 mm of Hg) for 4 hours while removing the MMA-methanol of reaction azeotrope. The progress of the reaction was monitored by refractive index analysis of the MMA-methanol of reaction distillate. During the reaction stage of the batch the temperature at the top of the column was 57.6 to 91.2°C and the temperature in the pot was 99 to 106°C. The conversion of E20CSA to E20CSMA was determined to be 94.9 % based on the methanol of reaction - MMA azeotrope removal and its analysis for methanol content by refractive index. The MMA was removed in vacuo (pot temperature / pressure of 45 to 109°C / 62 to 45 mm of Hg) from the stirred and 8% O₂ - 92% N₂ sparged mixture. The stirred mixture was cooled to 45°C and 4.10 grams (0.028 moles) of 2-ethyl hexanediol was added. The mixture was stirred and the solution temperature was maintained at 51 to 53°C for 1 hour. To the mixture was added 125.16 grams (1.454 moles) of glacial methacrylic acid. The mixture was stirred for 35 minutes and to it was added 62.6 grams (3.48 moles) of water. The cloud point of the product, an orange liquid, was 52°C. The cloud point was determined by preparing a solution of product in DI water (weight ratio of 1 part product to 99 parts water) and heating the stirred mixture to the point where the mixture became cloudy. The lowest temperature at which the mixture became cloudy was registered as the cloud point.

Example 6 - Polyethoxy cetyl-stearyl methacrylate with lithium hydroxide catalyst

[0023] A mixture of 400.0 grams (0.35 moles) of E20CSA that contained 1,021 ppm of p-methoxy phenol (MEHQ), 250.0 grams (2.5 moles) of methyl methacrylate (MMA), 0.4 grams (0.00323 moles) of MEHQ, and 0.1 grams (0.0006 moles) of 4-hydroxy-2,2,6,6-tetramethylpiperidiny free radical was added to a 1 liter, 4-necked flask equipped with a thermocouple with temperature readout, mechanical stirrer, 8% O₂ - 92% N₂ sparge inlet and a 1 inch diameter 10 plate Oldershaw column fitted with a distillation head, distillate rate removal-vapor pressure temperature controller, and a graduated distillate receiver. The mixture was stirred, sparged with 8% O₂ - 92% N₂ at a rate of 7 to 35 ml. / min. and heated to reflux under reduced pressure (550 mm of Hg) for 0.75 hours while removing the MMA-water azeotrope. During the dehydration stage of the batch the temperature at the top of the column was 65.2 to 85.8°C and the temperature in the pot was 95 to 100° C. At the conclusion of the dehydration of the batch the solution was cooled to 50 to 70°C and to it was added 0.3 grams (0.007 moles) of lithium hydroxide monohydrate and 62.0 grams (0.62 moles) of MMA. The mixture was stirred, sparged with 8% O₂ - 92% N₂ at a rate of 7 - 35 ml. / min. and heated to reflux under reduced pressure (550 mm of Hg) for 2 hours 40 min. while removing the MMA-methanol of reaction azeotrope. The progress of the reaction was monitored by refractive index analysis of the MMA-methanol of reaction distillate. During the reaction stage of the batch the temperature at the top of the column was 58.0 to 87.1°C and the temperature in the pot was 95 to 106°C. The conversion of E20CSA to E20CSMA was calculated to be 115.3 % based on the methanol of reaction - MMA azeotrope removal and its analysis for methanol content by refractive index. The MMA was removed in vacuo (pot temperature / pressure of 55 to 113°C / 120 to 20 mm of Hg) from the stirred and 8% O₂ - 92% N₂ sparged mixture. The stirred mixture was cooled to 45°C to afford 423.7 grams of neat E20CSMA.

[0024] Some of the neat E20CSMA (141.3 grams) was mixed with 60.5 grams of glacial methacrylic acid for approximately 1/2 hr. at 30 to 45°C. The mixture was polish filtered by vacuum filtration to produce the product mixture of E20CSMA - methacrylic acid. The cloud point of the product, a white - tan liquid, was 51.5 °C.

[0025] Some of the neat E20CSMA (141.3 grams) was mixed with 40.4 grams of glacial methacrylic acid for approximately 1/2 hr. at 30 to 45°C. The mixture was stirred for approximately 1/2 hr. and to it was added 20.2 grams of water. The mixture was polish filtered by vacuum filtration to produce the product mixture of E20CSMA - methacrylic acid - water. The cloud point of the product, a white - tan liquid, was 52 to 52.5°C.

[0026] For Example 5, the conversion of E20CSA to E20CSMA was 94.9 %. For Example 6, the conversion of E20CSA to E20CSMA was 115.3 %. This data demonstrates that the lithium catalyst is more effective than the titanate catalyst in a transesterification reaction.

Example 7 - Polyethoxy lauryl - myristyl methacrylate

[0027] A mixture of 410.9 grams (0.35 moles) of E23LMA that contained 954 ppm of MEHQ, 213.5 grams (2.135 moles) of MMA, 0.1 grams (0.0011 moles) of DEHA and 0.41 grams (0.0033 moles) of MEHQ was added to a reactor set up as described in Example 1. The mixture was stirred, sparged with 8% O₂ - 92% N₂ and heated to reflux under reduced pressure (550 mm of Hg) for 40 minutes while removing the MMA-water azeotrope. During the dehydration stage of the batch the temperature at the top of the column was 83 to 92°C and the temperature in the pot was 105 to 111°C. At the conclusion of the dehydration of the batch the solution was cooled to 70°C and to it was added 2.38 grams (0.007 moles) of tetrabutyl titanate and 53 grams (0.53 moles) of MMA. The solution was stirred, sparged with 8% O₂ - 92% N₂ and heated to reflux under reduced pressure (550 mm of Hg) for 3.25 hours while removing the MMA-methanol of reaction azeotrope. The progress of the reaction was monitored by refractive index analysis of the MMA-

methanol of reaction distillate. During the reaction stage of the batch the temperature at the top of the column was 57.7 to 59.6°C and the temperature in the pot was 104 to 114°C. The conversion of E23LMA to E23LMMA was determined to be 99 % based on the methanol of reaction - MMA azeotrope removal and its analysis for methanol content by refractive index. The MMA was removed in vacuo (pot temperature / pressure of 47 to 108°C / 70 to 43 mm of Hg) from the stirred and 8% O₂ - 92% N₂ sparged mixture. The stirred mixture was cooled to 46°C and 1.02 grams (0.007 moles) of 2-ethyl hexanediol was added. The mixture was stirred and the solution temperature was maintained at 50 to 55°C for 1 hour. To the mixture was added 186.3 grams (2.16 moles) of glacial methacrylic acid and the product (627.7 grams), an orange liquid, had a cloud point of 54.4°C. The cloud point was determined by preparing a solution of product in DI water (weight ratio of 1 part product to 99 parts water) and heating the stirred mixture to the point where the mixture became cloudy. The lowest temperature at which the mixture became cloudy was registered as the cloud point.

Example 8 - MEEU / MMA

[0028] A mixture of 130.0 grams (1.0 mole) of HEEU, 563.6 grams (5.64 moles) of MMA, 0.25 grams (0.002 moles) of MEHQ, 0.5 grams (0.003 moles) of PTZ and 1.3 grams (0.0146 moles) of DEHA was added to a reactor set up as described in Example 1. The mixture was stirred, sparged with 8% O₂ - 92% N₂ at a rate of 4 ml. / min. and heated to reflux under reduced pressure (700 mm of Hg) for 50 minutes while removing the MMA-water azeotrope. During the dehydration stage of the batch the temperature at the top of the column was 90 to 98.2°C and the temperature in the pot was 100 to 101°C. At the conclusion of the dehydration of the batch the solution was cooled to 70°C and to it was added 4.18 grams (0.0168 moles) of dibutyl tin oxide, 0.3 grams (0.0034 moles) of DEHA and 100.2 grams (1.0 moles) of MMA. The mixture was stirred, sparged with 8% O₂-92% N₂ at a rate of 4 ml. / min. and heated to reflux under reduced pressure (700 mm of Hg) for 4 hours 38 minutes while removing the MMA-methanol of reaction azeotrope. The progress of the reaction was monitored by refractive index analysis of the MMA-methanol of reaction distillate. During the reaction stage of the batch the temperature at the top of the column was 64.4 to 97.6°C and the temperature in the pot was 100 to 104°C. The conversion of HEEU to MEEU was determined to be 95.0 % based on the methanol of reaction - MMA azeotrope removal and its analysis for methanol content by refractive index. According to HPLC, the product, an orange liquid, contained 27.2 weight % MEEU, 69.4 weight % MMA, 0.35 weight % HEEU, and 1.99 weight % MEMEU.

Example 9 - MEEU / MMA

[0029] A mixture of 260.3 grams (2.0 mole) of HEEU, 1,123.8 grams (11.24 moles) of MMA and 0.398 grams (0.0023 moles) of 4-hydroxy-2,2,6,6-tetramethyl piperidinyI free radical was added to a reactor set up as described in Example 5. The mixture was stirred, sparged with 8% O₂ - 92% N₂ at a rate of 6 to 7 ml. / min. and heated to reflux under reduced pressure (700 mm of Hg) for 25 minutes while removing the MMA-water azeotrope. During the dehydration stage of the batch the temperature at the top of the column was 89.8 to 99°C and the temperature in the pot was 100°C. At the conclusion of the dehydration of the batch the solution was cooled to 70°C and to it was added 8.32 grams (0.0335 moles) of dibutyl tin oxide and 93.0 grams (1.0 moles) of MMA. The mixture was stirred, sparged with 8% O₂ - 92% N₂ at a rate of 4 - 10 ml. / min. and heated to reflux under reduced pressure (700 mm of Hg) for 3 hours 38 minutes while removing the MMA-methanol of reaction azeotrope. The progress of the reaction was monitored by refractive index analysis of the MMA-methanol of reaction distillate. During the reaction stage of the batch the temperature at the top of the column was 63.4 to 98.7°C and the temperature in the pot was 100 to 104°C. The conversion of HEEU to MEEU was determined to be 96.7% based on the methanol of reaction - MMA azeotrope removal and its analysis for methanol content by refractive index. According to HPLC the product, an orange liquid, contained 28.7 weight % MEEU, 68.0 weight % MMA, 0.45 weight % HEEU, and 0.8 weight % MEMEU.

Example 10 - DCPOEM

[0030] A mixture of 194.0 grams (1.0 mole) of DCPOEA, 120.0 grams (1.2 moles) of MMA, 0.051 grams (0.0004 moles) of MEHQ and 0.049 grams (0.0003 moles) of 4-hydroxy-2,2,6,6-tetramethyl piperidinyI free radical was added to a 500 milliliter 4 necked flask equipped with a thermometer, mechanical stirrer, 8% O₂ - 92% N₂ sparge inlet and a 1 inch diameter - 10 plate Oldershaw column fitted with a distillation head, distillate rate removal-vapor pressure temperature controller, and a graduated distillate receiver. The mixture was stirred, sparged with 8% O₂ - 92% N₂ at a rate of 8 - 10 ml. / min. and heated to reflux under reduced pressure (400 mm of Hg) for 13 minutes while removing the MMA-water azeotrope. The temperature at the top of the column was 79.3 to 81.4°C and the temperature in the pot was 99 - 103°C. At the conclusion of the dehydration of the batch the solution was cooled to 70°C and to it was added 3.96 grams (0.007 moles) of tetraethylhexyl titanate and 25.0 grams (0.25 moles) of MMA. The mixture was stirred,

sparged with 8% O₂ - 92% N₂ at a rate of 4 - 7.5 ml. / min. and heated to reflux under reduced pressure (400 mm of Hg) for 9 hours. During the reaction stage the addition of MMA was made to the batch to help control batch temperature and maintain efficient column operation. The amount of the MMA charges and the elapsed reaction time were: 50 grams (0.5 moles) of MMA added after 2 1/2 hours of reaction time, followed by % hours. of reaction time, followed by the addition of 51 grams (0.51 moles) of MMA and the reaction continuation for 4 1/2 hours. while removing the MMA-methanol of reaction azeotrope. The progress of the reaction was monitored by refractive index analysis of the MMA-methanol of reaction distillate. The temperature at the top of the column was 49.2 to 81.1°C and the temperature in the pot was 99 to 115°C. The conversion of the DCPOEA to DCPOEM was estimated to be 95% based on the methanol of reaction - MMA azeotrope removal and its analysis by refractive index. The MMA was removed in vacuo (pot temperature / pressure of 22 to 88°C / 50 to 20 mm of Hg) from the stirred and 8% O₂ - 92% N₂ sparged mixture. The resulting product was isolated (266.1 grams) and analyzed. GLC analysis showed 95.5 area % DCPOEM, 0.63 area % DCPOEA, 0.46 area % MMA and 1.84 area % ethyl hexyl methacrylate (catalyst byproduct).

Example 11 - DCPOEM - distilled grade

[0031] A mixture of 291.0 grams (1.5 mole) of DCPOEA, 238.5 grams (2.39 moles) of MMA, 0.074 grams (0.0006 moles) of MEHQ and 0.074 grams (0.00043 moles) of 4-hydroxy-2,2,6,6-tetramethyl piperidiny free radical was added to a reactor set up as described in Example 1. The mixture was stirred, sparged with 8% O₂ - 92% N₂ and heated to reflux under reduced pressure (400 mm of Hg) for 16 minutes while removing the MMA-water azeotrope. The temperature at the top of the column was 79.9 to 82.6°C and the temperature in the pot was 96 - 103°C. At the conclusion of the dehydration of the batch the solution was cooled to 70°C and to it was added 5.93 grams (0.0105 moles) of tetraethylhexyl titanate and 10.0 grams (0.1 moles) of MMA. The mixture was stirred, sparged with 8% O₂ - 92% N₂ and heated to reflux under reduced pressure (400 mm of Hg) for 5 hrs. During the reaction stage the addition of MMA was made to the batch to help control batch temperature and maintain efficient column operation. The amount of the MMA charges and the elapsed reaction time were: 56.8 grams (0.568 moles) of MMA added after 2 hrs. of reaction time, followed by 1 hr. of reaction time, followed by the addition of 25.4 grams (0.254 moles) of MMA and 1 hr. of reaction time, followed by the addition of 48.3 grams (0.483 moles) of MMA and the reaction continuation for 1 hr. while removing the MMA-methanol of reaction azeotrope. The progress of the reaction was monitored by refractive index analysis of the MMA-methanol of reaction distillate. The temperature at the top of the column was 49.1 to 82.2°C and the temperature in the pot was 100 to 119°C. The conversion of the DCPOEA to DCPOEM was estimated to be 98% based on the methanol of reaction - MMA azeotrope removal and its analysis by refractive index. A mixture of 0.073 grams (0.00043 moles) of 4-hydroxy-2,2,6,6-tetramethyl piperidiny free radical and the reaction mixture was fractionally vacuum distilled. The major fraction (290.8 grams), a colorless clear liquid, was obtained during the distillation (vapor temperature range/ pot temperature range / pressure of 126 to 135°C / 154 - 160°C / 1. mm of Hg.). Earlier distillation fractions (73.44 grams) contained 62 - 93.6 area % DCPOEM by GLC analysis and the still bottoms (33.05 grams) was not analyzed. GLC analysis showed that the major fraction contained 96.9 area % DCPOEM, < 0.1 area % DCPOEA, < 0.1 area % MMA and < 0.1 area % ethyl hexyl methacrylate (catalyst byproduct).

Example 12 - Oxazolidinylethyl Methacrylate - Continuous Process

[0032] MMA containing 2,000 ppm PTZ and 200 ppm MEHQ was fed to a 189 liter flash drum at the base of a 32 tray distillation column at 235 pounds per hour. The MMA was refluxed up the column at approximately 500 mm Hg vacuum. An inhibitor stream containing 5% PTZ and 2.5% MEHQ in MMA was fed into the top of the column at 1 pound per hour. HEOX was fed to the distillation column at the 28th tray from the base at 160 pounds per hour. Methanolic magnesium methylate (8%) catalyst was fed to the 20th tray from the base of the column at 43 pounds per hour. Trays between the 28th tray from the base and the 20th tray from the base were used to azeotropically dehydrate water from the HEOX. The refluxing MMA azeotropically carried the methanol coproduct to the top of the column, driving the reaction forward. The reflux ratio was adjusted to give a head temperature of from 66 to 72° C. Steam pressure on the reboiler at the base of the column was adjusted to from 115 to 117° C. After an hour, 6th plate analysis showed 74% MMA, 27% OXEMA, and less than 1% HEOX. The column overheads comprising MMA, methanol, and water azeotropes were collected for recovery of the MMA. The column bottoms were continuously stripped and the MMA overheads recycled to the base of the column. The stripped bottoms were then continuously rectified to give 230 pounds per hour of 95% pure OXEMA.

Example 13 - 2-Isopropyl-3-hydroxyethyl-oxazolidine Bis-ester

[0033] To a 2-liter round bottom, four neck flask equipped with a thermocouple/temperature controller, stirrer, constant

pressure addition funnel, N₂ sparge, and a reflux condenser with a straight lead distillation head was added 206.6 g of 97.2% pure IPOX. The IPOX was heated to 89° C to 103° C with sparging for 2 hours. The IPOX was cooled to 35° C. Through the addition funnel, 11.5 g of 15% potassium t-butoxide in t-butanol was added with stirring. The stirred flask was heated to 92.5° C over 16 minutes. To the heated solution was added 100.2 g of mixed DBE dropwise over 30 minutes at a temperature range of from 91.1 to 94.7° C. The stirred reactor was held at from 91.1 to 94.9° C under 137 to 210 mm Hg for 90 minutes. The batch was analyzed. paralyis indicated 97.2% IPOX and 2.7% high molecular weight impurities. The batch was stirred for 20 minutes at 94.9 to 95.5° C and 139 mm Hg. The batch was cooled to 80° C and 5.8 g of 15% potassium t-butoxide in t-butanol was added. The reactor was heated at 91.4 to 97.4° C under 96 mm Hg for 1 hour. Analysis showed 74.1% bis ester of IPOX, 11.2% half ester of IPOX, 12.2% IPOX, and 2.5% high molecular weight impurities. The stirred reactor was heated at 94.4 to 97.4° C at 96 mm Hg for another hour. Analysis showed 77.1% bis ester of IPOX, 9.4% half ester of IPOX, 11.1% IPOX, and 2.4% high molecular weight impurities. The batch was cooled to 60° C over 45 minutes. To the batch was added 163.1 g heptane, followed by 71.6 g water and 2.4 g sulfuric acid. The entire mixture was then transferred to a separatory funnel and allowed to stand overnight. The aqueous layer was drained off. The organic layer was returned to the flask, and the heptane was stripped off at 700 mm Hg and 60 to 84° C over 2 hours. Analysis of the final product showed 76.5% bis ester of IPOX, 10.7% half ester of IPOX, 8.5% IPOX, and 3.5% high molecular weight impurities.

Example 14 - Preparation of 4-Methacryloyloxy-2,6,6-tetramethyl piperidinyI free radical

[0034] A mixture of 250.3 grams (2.5 moles) of methyl methacrylate (MMA), 0.4 grams (0.00323 moles) of MEHQ and 86.85 grams (0.0.504 moles) of 4-hydroxy-2,2,6,6-tetramethyl piperidinyI free radical ("4-hydroxy TEMPO") were added to a 1 liter 4-necked flask equipped with a thermocouple with temperature readout, mechanical stirrer and a 1 inch (2.54 cm) diameter 10 plate Oldershaw column fitted with a distillation head, distillate rate removal-vapor pressure temperature controller, and a graduated distillate receiver. The mixture was stirred and heated to reflux under reduced pressure (700 mm of Hg) for 0.5 hours while removing the MMA-water azeotrope. During the dehydration stage of the batch the temperature at the top of the column was 86.9 to 97.3°C and the temperature in the pot was 104°C. At the conclusion of the dehydration of the batch 5.65 grams (0.01 mole) of tetraethylhexyl titanate was added. The mixture was stirred and heated to reflux under reduced pressure (700 mm of Hg) for 2 hours, while removing the MMA-methanol of reaction azeotrope. The progress of the reaction was monitored by refractive index analysis of the MMA-methanol of reaction distillate. During the reaction stage of the batch the temperature at the top of the column was 63.9 to 99.7°C and the temperature in the pot was 98 to 108°C. The conversion of 4-hydroxy-TEMPO to 4-methacryloyloxy-2,6,6-tetramethyl piperidinyI free radical ("4-HT methacrylate") was calculated to be 96.8 % based on the methanol of reaction - MMA azeotrope removal and its analysis for methanol content by refractive index. The reaction mixture was allowed to stand at ambient temperature overnight and the suspension formed was decanted. The crystalline solid was air dried to yield a first crop of 6.54 grams of 4-HT methacrylate. The MMA was removed from the filtrate on a rotary evaporator and the solid residue was washed with heptane and air dried to yield a second crop of 33.2 grams of 4-HT methacrylate. According to quantitative high-performance liquid chromatography (HPLC) the heptane washed and dried solid contained 99.2 % 4-HT methacrylate. The melting point of the product was 85-86.5 °C.

Example 15 - Preparation of 4-Hydroxy-2,6,6-tetramethyl N-hydroxy piperidine

[0035] To a stirred solution of 126.52 grams (0.735 moles) of 4-hydroxy-2,2,6,6-tetramethyl piperidinyI free radical in 632.64 grams (6.32 moles) of methyl methacrylate was added 65.4 grams (0.73 moles) of N,N-diethyl hydroxylamine. The mixture was stirred at ambient temperature for approximately 5 hrs. and allowed to stand at ambient temperature overnight. The suspension was vacuum filtered. The filter cake was washed with MMA and air dried to yield 88.06 grams of 4-hydroxy-2,6,6-tetramethyl N-hydroxy piperidine. The melting point of this product was 55-157 °C.

Example 16 - Inhibitor Effectiveness

[0036] A Base Stock of 660 g of the monomer composition from Example 8, 0.167 mole % (standard amount) DBTO as catalyst and 60.6 ppm (0.2x standard amount) of 4-hydroxy TEMPO as inhibitor was prepared. Four 100 ml one-neck boiling flasks were each set up with a magnetic stir bar and fitted with Y adapter, pot thermometer, West condenser, and heating mantle controlled by a rheostat (set at 65 volts) plugged into a Thermowatch temperature control device. Each flask was charged with a 40 g mixture as follows:

Flask # 1	Base Stock
Flask # 2 (Comparative)	Base Stock with an extra 300 ppm 4-hydroxy TEMPO added.

(continued)

Flask # 3	Base Stock with 300 ppm 4-HT methacrylate added.
Flask # 4	Base Stock with 300 ppm 4-hydroxy-2,6,6-tetramethyl N-hydroxy piperidine added.

[0037] All of the above samples were maintained at 92-95°C with agitation and were open to the atmosphere. All samples ran continuously (overnight) at the conditions stated during weekdays, but were cooled to room temperature for the weekend. Samples were tested for soluble polymer by methanol and butyl acrylate ("BA") dilution tests at least twice a day. Methanol and BA dilution tests were conducted using a 1:10 ratio of sample to diluent. The samples passed the soluble polymer tests if a clear solution was obtained. The samples failed the soluble polymer tests if haziness or cloudiness was observed. These results are reported below.

Dilution Test	Flask	Time to Fail (hours)
Methanol	1	24
	2	164
	3	132
	4	132
BA	1	24
	2	157
	3	132
	4	115.5

[0038] The above data clearly show that 4-methacryloyloxy-2,6,6-tetramethyl piperidiny free radical and 4-hydroxy-2,6,6-tetramethyl N-hydroxy piperidine are effective inhibitors of unwanted monomer polymerization.

Claims

1. A process comprising:

a) forming a reaction mixture by admixing:

- 1) an alcohol selected from the group consisting of hydroxyethyl ethylene urea, ethoxylated cetyl-stearyl alcohol, ethoxylated lauryl-myristyl alcohol, dicyclopentenylloxyethyl alcohol, and hydroxyethyl oxazolidine;
- 2) from 10 to 10,000 parts per million based on the alcohol charge of at least one inhibitor selected from the group consisting of diethylhydroxylamine, p-methoxy phenol, hydroquinone, phenothiazine, 4-hydroxy-2,2,6,6-tetramethyl piperidiny free radical, 4-methacryloyloxy-2,6,6-tetramethyl piperidiny free radical, and 4-hydroxy-2,6,6-tetramethyl N-hydroxy piperidine;
- 3) methyl methacrylate, wherein the mole ratio of alcohol to methyl methacrylate is from 1:1 to 1:20; and
- 4) from 0.1 to 10 mole percent of a catalyst selected from the group consisting of dibutyl tin oxide, reaction products of dibutyl tin oxide with components in the transesterification of various alcohols with alkyl (meth)acrylates; dibutyl tin dimethoxide, reaction products of dibutyl tin dimethoxide with components in the transesterification of various alcohols with alkyl (meth)acrylates; methanolic magnesium methylate; lithium, lithium carbonate, and lithium hydroxide;

b) reacting the alcohol with the methyl methacrylate at a temperature of from 60 to 140°C and a pressure of from 400 mm Hg to 760 mm Hg;

c) creating a crude product by azeotropically removing a mixture of methyl methacrylate and methanol;

d) optionally adding water to enable recycling of the catalyst;

e) optionally recycling the methyl methacrylate; and

f) optionally distilling the crude product.

2. A process according to claim 1 wherein:

- a) the amount of the inhibitor is from 100 to 5,000 parts per million based on the alcohol charge;
- b) the mole ratio of alcohol to methyl methacrylate is from 1:1 to 1:15;
- c) the amount of the catalyst is from 0.5 to 7 mole percent; and
- d) the reaction is run at a temperature of from 70-125°C.

3. A process according to claim 1 wherein:

- a) the amount of the inhibitor is from 200 to 3,000 parts per million based on the alcohol charge;
- b) the mole ratio of alcohol to methyl methacrylate is from 1:1.2 to 1:10;
- c) the amount of the catalyst is from 1 to 5 mole percent; and
- d) the reaction is run at a temperature of from 100-120°C.

4. A process according to claim 3 wherein the catalyst is lithium hydroxide.

5. A compound selected from the group consisting of 4-methacryloyloxy-2,6,6-tetramethyl piperidinyI free radical and 4-hydroxy-2,6,6-tetramethyl N-hydroxy piperidine.

6. A composition comprising at least one monomer selected from the group consisting of N-(2-methacryloyloxyethyl) ethylene urea, ethoxylated cetyl-stearyl methacrylate, ethoxylated lauryl-myristyl methacrylate, dicyclopentenyl-methacrylate, and oxazolidinylethyl methacrylate and at least one compound selected from the group consisting of 4-methacryloyloxy-2,6,6-tetramethyl piperidinyI free radical and 4-hydroxy-2,6,6-tetramethyl N-hydroxy piperidine.

7. A method of inhibiting the unwanted polymerization of a monomer comprising combining with said monomer at least one compound selected from the group consisting of 4-methacryloyloxy-2,6,6-tetramethyl piperidinyI free radical and 4-hydroxy-2,6,6-tetramethyl N-hydroxy piperidine.

8. An inhibited monomer composition prepared according to the process of claim 1.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 30 6833

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	EP 0 453 638 A (RÖHM GMBH) 30 October 1991 * page 3, line 36 - page 4, line 29 * * page 4; example * * page 4 - page 5; claims * ---	1-3,5-8	C07D233/32 C07C67/03 C07C69/54 C07C67/62 C07D263/04
X	EP 0 433 135 A (ATOCHEM) 19 June 1991 * page 3, line 9 - page 4, line 25 * * page 5; examples * * page 5 - page 6; claims * ---	1-3	
X	EP 0 650 962 A (ELF ATOCHEM) 3 May 1995 * page 2, line 1 - line 41 * * page 2, line 1 - line 42 * * page 4; example 1 * * page 5 - page 6; claims * ---	1-3	
X	EP 0 571 851 A (RÖHM GMBH) 1 December 1993 * page 3, line 41 - page 4, line 37 * * page 5, line 27 - page 6, line 12 * * page 6; examples 1-3 * * page 7 - page 8; claims * ---	1-4	
X	DE 196 02 035 A (RÖHM GMBH) 24 July 1997 * page 2, line 56 - page 3, line 33 * * page 3, line 58 - page 4, line 8 * * page 4 - page 5; examples 1-3 * * page 5 - page 6; claims * ---	1-3	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C07D C07C
X	US 5 072 027 A (AKIHIRO KOBAYASHI) 10 December 1991 * column 4, line 1 - line 64 * * column 5 - column 10; examples 1,3 * * column 18 - column 20; claims * --- -/--	1-4	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 3 December 1998	Examiner Kinzing, J
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03 82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 30 6833

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	JAROSLAV BARTON ET AL.: "Partitioned polymerization, 3: On the use of inhibitors partially soluble in the aqueous phase" MAKROMOLEKULARE CHEMIE, MACROMOLECULAR CHEMISTRY AND PHYSICS., vol. 190, no. 4, April 1989, pages 769-775, XP002086582 BASEL CH * page 769 summary, page 770-771 experimental part, page 772 table 1 *	5-8	
X	TERRY D. LEE ET AL.: "In Situ Reduction of Nitroxyde Spin Labels with Phenylhydrazine in Deuteriochloroform Solution. A Convenient Method for Obtaining Structural Information on Nitroxides Using Nuclear Magnetic Resonance Spectroscopy" JOURNAL OF ORGANIC CHEMISTRY., vol. 40, no. 21, 17 October 1975, pages 3145-3147, XP002086583 EASTON US * page 3145, right-hand column, last paragraph * * compound 2 * * page 3146 *	5	
A	US 3 037 006 A (ELINOR M. HANKINS) 29 May 1962 * column 1, line 12 - column 2, line 10 * * column 4 - column 5; example 1 * * column 9; claim 17 *	1	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 3 December 1998	Examiner Kinzinger, J
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503/03.02 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 30 6833

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

03-12-1998

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 453638	A	30-10-1991	DE 4010532 A	10-10-1991
EP 433135	A	19-06-1991	FR 2655987 A	21-06-1991
			AT 118486 T	15-03-1995
			CA 2032355 A	16-06-1991
			DE 69016966 D	23-03-1995
			DE 69016966 T	13-07-1995
			DK 433135 T	03-04-1995
			ES 2068364 T	16-04-1995
			GR 3015795 T	31-07-1995
			JP 4330063 A	18-11-1992
			US 5210199 A	11-05-1993
EP 650962	A	03-05-1995	FR 2711653 A	05-05-1995
			AU 683087 B	30-10-1997
			AU 7745594 A	18-05-1995
			CA 2134430 A	28-04-1995
			CN 1105992 A	02-08-1995
			CZ 9402657 A	17-05-1995
			FI 945030 A	28-04-1995
			JP 2818640 B	30-10-1998
			JP 7188179 A	25-07-1995
			KR 9711457 B	11-07-1997
			NO 944078 A	28-04-1995
			US 5498723 A	12-03-1996
			ZA 9408480 A	20-06-1995
EP 571851	A	01-12-1993	DE 4217124 A	25-11-1993
			AT 136889 T	15-05-1996
			DE 59302230 D	23-05-1996
			ES 2087607 T	16-07-1996
			US 5567826 A	22-10-1996
DE 19602035	A	24-07-1997	WO 9726293 A	24-07-1997
			EP 0874870 A	04-11-1998
US 5072027	A	10-12-1991	JP 2101042 A	12-04-1990
			JP 2101043 A	12-04-1990
			JP 2101044 A	12-04-1990
US 3037006	A	29-05-1962	DE 1243393 B	08-04-1963
			FR 1313754 A	
			GB 992721 A	
			NL 120763 C	
			NL 266645 A	

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82